



COMPOUND DATA SHEET

Parker O-Ring & Engineered Seals Division (OES) North America

MATERIAL REPORT

LTR: 1013111

Title: Evaluation of Parker Compound E0803-70

Elastomer Type: Ethylene-Propylene Rubber (EPR, EPDM)

Purpose: To obtain typical test data.

Specification: ASTM D2000 M4CA710 A25 B35 EA14 Z1 (Specific Gravity Report) Z2 (Low Temperature Resistance Report)

Color: Black

Recommended Temperature Range: -70°F to 250°F

Recommended For: Hot water and steam up to 300°F, glycol based brake fluids (DOT3 and DOT4), silicone based brake fluids (DOT5), many organic and inorganic acids, cleaning agents, sodium and potassium alkalis, many polar solvents (alcohols, ketones, esters), ozone, aging and weather resistant.

Not Recommended For: Mineral oil products (oils, greases and fuels)

Additional Approvals: N/A

Parker O-Ring & Engineered Seals Division (OES) North America

REPORT DATA

<u>Original Physical Properties</u>	<u>Test Method</u>	<u>Spec Limits</u>	<u>Test Results</u>
Hardness, Shore A, pts.	ASTM D2240	70 ± 5	75
Tensile Strength, psi. min	ASTM D412	1450	2197
Ultimate Elongation, %	ASTM D412	180	216
Specific Gravity (Z1)	ASTM D297	report	1.15

(A25) Dry Heat Resistance, 70 hrs. @ 257°F

Hardness Change, pts	ASTM D573	± 15	+ 1
Tensile Change, %		± 30	+ 4
Elongation Change, %		± 50	+ 5

(B35) Compression Set (Plied), 22 hrs. @ 257°F

Percent of Original Deflection, max	ASTM D395 Method B	70	7
-------------------------------------	--------------------	----	---

(EA14) Fluid Immersion, H2O, (70 hrs. @ 212°F)

Volume Change, %	ASTM D471	± 5	+ 1
------------------	-----------	-----	-----

Low Temperature Resistance (Z2)

TR-10 degrees C	ASTM D1329	report	- 43
-----------------	------------	--------	------

“Purchaser use only. Reproduce in full. Data pertains to items referenced only”
“The recording of false, fictitious, or fraudulent statements or entries in this report may be punishable as a felony under federal law”