



COMPOUND DATA SHEET

Parker O-Ring Division, North America

MATERIAL REPORT

LTR Report Number: 95609
Date: 7/11/2013

Title: Evaluation of Parker Compound S1224-70

Elastomer Type: Silicone (VMQ, PVMQ)

Purpose: To obtain typical test data.

Specification: ASTM D2000 M7GE705 A19 B37 EA14 E016 E036 F19 G11 Z1 (Specific Gravity)

Color: Rust

Recommended Temperature Range: -65°F to 450°F

Recommended For: Animal, Vegetable oil, and grease, high molecular weight chlorinated aromatic hydrocarbons (including flame-resistant insulators, and coolant for transformers), moderate water resistance, diluted salt solutions, ozone, aging, and weather resistance.

Not Recommended For: Superheated water/steam over 250°F, acids and alkalis, low molecular weight chlorinated hydrocarbons (trichloroethylene), hydrocarbon based fuels, aromatic hydrocarbons (benzene, toluene), low molecular weight silicone oils.

Additional Approvals: AMS 3304
AMS 3357
MIL-G-21569 Class 2
A-A-59588 Class 2a, 2b, Grade 70

REPORT DATA

<u>Original Physical Properties</u>	<u>Test Method</u>	<u>Spec Limits</u>	<u>Test Results</u>
Hardness, Shore A, pts.	ASTM D2240	70 ±5	70
Tensile Strength, PSI	ASTM D412	725	1094
Ultimate Elongation, %	ASTM D412	150	217
(Z1) Specific Gravity	ASTM D297	report	
(B37) Compression Set (Plied)			
<u>22 hrs. @ 347°F</u>			
Percent of Original Deflection, Max	ASTM D395 Method B	30	24
(A19) Heat Age			
<u>70 hrs. @ 437°F</u>			
Hardness Change, pts.	ASTM D573	+10	+5
Tensile Strength Change, %		-25	-21
Ultimate Elongation Change, %		-30	-20
(EA14) Fluid Resistance			
<u>Water, 70 hrs @ 212°F</u>			
Hardness Change, pts.	ASTM D471	± 5	+4
Volume Change, %		± 5	-1
(E016) Fluid Resistance			
<u>IRM 901, 70 hrs @ 302°F</u>			
Hardness Change, pts.	ASTM D471	-0 to -15	-5
Tensile Strength Change, %		-20	+6
Ultimate Elongation Change, %		-20	+8
Volume Change, %		0 to +15	+4
(E036) Fluid Resistance			
<u>IRM 903, 70 hrs @ 302°F</u>			
Hardness Change, pts.	ASTM D471	-40	-22
Volume Change, %		+60	+35
(G11) Tear Resistance			
<u>kN/m, min.</u>	ASTM D624	9	21
<u>(F19) Low Temperature Resistance</u>			
Nonbrillite after 3 min @ -67°F	ASTM D1329	pass/fail	Pass

"Purchaser use only. Reproduce only in full. Data pertains to items referenced only."

"The recording of false, fictitious, or fraudulent statements or entries in this report may be punishable as a felony under federal law."