


CS: 5.70 mm  $\pm 0.15$  mm (0.224"  $\pm 0.006$ " )  
ID: 84.20 mm  $\pm 0.71$  mm (3.315"  $\pm 0.028$ " )

 ALL-AROUND BETTER	PART NUMBER	<b>E5.70X084.2</b>
	EPDM 70 Duro Metric O-Ring 5.70 mm CS X 84.20 mm ID	
14450 John F. Kennedy Blvd.      www.globaloring.com Houston, TX 77032		
Information in this drawing is provided for reference only		

<b>Compound</b>	E70-B101	EPDM, Black, General Purpose
	Temperature Range (Static):	-55°C to 125°C
	Specification:	M3CA707 A25 B35 EA14 F17

		Required Results	Typical Results
<b>Properties</b>	Hardness, (Shore A)	70±5	69
	Tensile Strength, psi(MPa)	1015(7)(min)	1644(11.34)
	Elongation, (%)	200(min)	333
	Modulus at 100%, psi(MPa)		782(5.39)
	Density, (Mg/m <sup>3</sup> )		1.27
<b>A25</b>	Hardness Change, pts.	+10(max)	+3
	Tensile Strength Change, %	-20(max)	+10
	Elongation Change, %	-40(max)	-34
	Weight Change, %		+0.1
<b>B35</b>	-	70%(plied)(max)	48.9
<b>EA14</b>	Hardness Change, pts.		+1
	Tensile Strength Change, %		0
	Elongation Change, %		-22
	Volume Change, %	±5	+1.6
<b>F17</b>	(ASTM D2137-11, Method C)		
	Sample type: T-50,		
	Coolant : Isopropyl alcohol		
	Low Temperature Property,	pass	pass