


CS: 3.50 mm  $\pm 0.10$  mm (0.138"  $\pm 0.004$ ")  
ID: 49.70 mm  $\pm 0.45$  mm (1.957"  $\pm 0.018$ ")

 ALL-AROUND BETTER	PART NUMBER <b>V3.50X049.7</b>
14450 John F. Kennedy Blvd. Houston, TX 77032 <a href="http://www.globaloring.com">www.globaloring.com</a>	Viton 75 Duro Metric O-Ring 3.50 mm CS X 49.70 mm ID
Information in this drawing is provided for reference only	

<b>Compound</b>	V75-B101	Genuine Viton®, General Purpose
	Temperature Range (Static):	-25°C to 250°C
	Cure System:	Bisphenol
	Specification:	M4HK715 A1-10 B37 B38 EF31 EO78 Z1

Compound Previously Known As: V75101

		Required Results	Typical Results
<b>Properties</b>	Hardness, Shore A, pts	75±5	77
	Tensile Strength, psi, min	1450(min)	2077
	Elongation, min, %	175(min)	175
	Modulus @ 100%, psi	D412-16	1125
	Density, Mg/m3		1.84
<b>A1-A10</b>	Hardness Change, pts, Shore A	+10(max)	+1
	Tensile Strength Change, %	-25(max)	-2
	Elongation Change, %	-25(max)	-8
	Weight Change, %		-1.7
<b>B37</b>	ASTM D395-18, Method B	50%(plied)(max)	7.3
<b>B38</b>	ASTM D395-18, Method B	50%(plied)(max)	8.1
<b>EF31</b>	Hardness Change, pts, Shore A	±5	-2
	Tensile Strength Change, %	-25(max)	-19
	Elongation Change, %	-20(max)	-5
	Volume Change, %	0~+10	+3.1
<b>EO78</b>	Hardness Change, pts, Shore A	-15~+5	-6
	Tensile Strength Change, %	-40(max)	-16
	Elongation Change, %	-20(max)	+1
	Volume Change, %	0~+15	+9.5