



# MATERIAL DATA SHEET

Global O-Ring and Seal, LLC

COMPOUND	V75-B108	MATERIAL	FKM
DUROMETER	75 Shore A	COLOR	Black
DESIGNATION	Viton GLTS	REPORT DATE	2021-05-17
TEMP RANGE	-	CURE SYSTEM	-
SPECIFICATION	ASTM D2000 M2HK710 A1-10 B37 B38 EF31 EO78 F17		

## PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	CONDITION	UNITS	RESULT	REQUIREMENT
(Z1) Hardness (Shore A)	D2240-15 <sup>E1</sup>	-	Shore A	76	75 ±5
Tensile Strength	D412-16	-	MPa (PSI)	16.6 (2,413)	10 (1,450) min
Elongation at Break	D412-16	-	%	270	175 min
100% Modulus	D412-16	-	MPa (PSI)	5.4 (783)	-
Density	CNS 5341-96, Method A	-	Mg/m <sup>3</sup>	1.84	-

## A1-10 – HEAT RESISTANCE

PROPERTY	TEST METHOD	CONDITION	UNITS	RESULT	REQUIREMENT
Hardness Change	D573-04	70 Hrs @ 250°C (482°F)	points	1	10 max
Tensile Strength Change	D573-04	70 Hrs @ 250°C (482°F)	%	-9	-25 max
Elongation Change	D573-04	70 Hrs @ 250°C (482°F)	%	28	-25 max
Weight Change	D573-04	70 Hrs @ 250°C (482°F)	%	-2.1	-

## B37 – COMPRESSION SET

PROPERTY	TEST METHOD	CONDITION	UNITS	RESULT	REQUIREMENT
Compression Set	D395-18, Method B	22 Hrs @ 175°C (347°F) (plied)	%	14.3	50 max

## B38 – COMPRESSION SET

PROPERTY	TEST METHOD	CONDITION	UNITS	RESULT	REQUIREMENT
Compression Set	D395-18, Method B	22 Hrs @ 200°C (392°F) (plied)	%	17.4	50 max

## EF31 – FLUID RESISTANCE, ASTM FUEL C RESISTANCE

PROPERTY	TEST METHOD	CONDITION	UNITS	RESULT	REQUIREMENT
Hardness Change	D471-16a	70 Hrs @ 23°C (73°F)	points	-5	±5
Tensile Strength Change	D471-16a	70 Hrs @ 23°C (73°F)	%	-24	-25 max

PROPERTY	TEST METHOD	CONDITION	UNITS	RESULT	REQUIREMENT
Elongation Change	D471-16a	70 Hrs @ 23°C (73°F)	%	<b>-13</b>	-20 max
Volume Change	D471-16a	70 Hrs @ 23°C (73°F)	%	<b>6.6</b>	0 to 10

**E078 – FLUID RESISTANCE, ASTM NO. 101 OIL**

PROPERTY	TEST METHOD	CONDITION	UNITS	RESULT	REQUIREMENT
Hardness Change	D471-16a	70 Hrs @ 200°C (392°F)	points	<b>-11</b>	-15 to 5
Tensile Strength Change	D471-16a	70 Hrs @ 200°C (392°F)	%	<b>-15</b>	-40 max
Elongation Change	D471-16a	70 Hrs @ 200°C (392°F)	%	<b>-3</b>	-20 max
Volume Change	D471-16a	70 Hrs @ 200°C (392°F)	%	<b>13</b>	0 to 15

**F17 – LOW-TEMPERATURE RESISTANCE**

PROPERTY	TEST METHOD	CONDITION	UNITS	RESULT	REQUIREMENT
Low Temperature Brittleness	D2137-11,Method C	3 minute @ -40°C (-40°F)	-	<b>pass</b>	pass

**ADDITIONAL APPROVALS**

-
---

Data shown is based on supplier testing of compound slabs/buttons and is provided for general reference only.